

Grilon® EB 50 H DZ

Polyamide 6

EMS-GRIVORY

Message:

Grilon® EB 50 H DZ is a Polyamide 6 (Nylon 6) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for blow molding or extrusion.

Important attributes of Grilon® EB 50 H DZ are:

- Flame Rated
- RoHS Compliant
- Heat Stabilizer
- High Viscosity
- Impact Modified

Typical applications include:

- Automotive
- Consumer Goods
- Electrical/Electronic Applications
- Hose/Tubing
- Industrial Applications

General Information				
Additive		Heat Stabilizer		
		Impact Modifier		
Features		Heat Stabilized		
		High Viscosity		
		Impact Modified		
Uses		Automotive Applications		
		Blow Molding Applications		
		Consumer Applications		
		Electrical/Electronic Applications		
		Hydraulic Applications		
		Industrial Applications		
		Pneumatic Applications		
		Tubing		
		Wire & Cable Applications		
RoHS Compliance		RoHS Compliant		
Forms		Granules		
Processing Method		Blow Molding		
		Extrusion		
Multi-Point Data		Shear Modulus vs. Temperature (ISO 11403-1)		
Physical	Dry	Conditioned	Unit	Test Method

Density	1.10	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
Saturation, 23°C	9.0	--	%	
Equilibrium, 23°C, 50% RH	3.0	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	100	40.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2300	700	MPa	ISO 527-2
Tensile Stress (Yield)	60.0	35.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.0	20	%	ISO 527-2
Nominal Tensile Strain at Break	50	> 50	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	20	20	kJ/m ²	
23°C	70 kJ/m ²	No Break		
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	90.0	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	--	°C	ISO 75-2/A
Continuous Use Temperature				Internal Method
-- ¹	100 to 120	--	°C	
-- ²	180	--	°C	
Melting Temperature ³	222	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.2E-4	--	cm/cm/°C	
Transverse	1.4E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+13	1.0E+11	ohms·cm	IEC 60093
Electric Strength	27	24	kV/mm	IEC 60243-1
Comparative Tracking Index	--	425	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method

ISO Type	PA 6-HI, BH, 34-020	--	ISO 1874
NOTE			
1.	Long Term		
2.	Short Term		
3.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

