

KURARISTER™ C

Polyethylene Terephthalate

Kuraray Co., Ltd.

Message:

KURARISTER™ C has tensile properties similar to those of PET with better elongation than PET film.

General Information			
Features	Gas Barrier		
Uses	Film		
Forms	Film		
Films	Nominal Value	Unit	Test Method
Elastic Modulus - MD ¹	5400	MPa	ASTM D882
Elastic Modulus - TD ²	5100	MPa	ASTM D882
Tensile Strength ³			ASTM D882
MD : Break	220	MPa	
TD : Break	170	MPa	
Tensile Elongation ⁴			ASTM D882
MD : Break	120	%	
TD : Break	170	%	
NOTE			
1.	23°C, 50%RH		
2.	23°C, 50%RH		
3.	23°C, 50%RH		
4.	23°C, 50%RH		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

