

Nymax™ 600 A Natural

Polyamide 6 Alloy

PolyOne Corporation

Message:

Nylon 6 Nymax® 600 blend series products are "salt and pepper" pellet blends, including nylon resin, processing aids, performance modifiers and color masterbatches. According to different grades, these materials are dedicated to improving melt processing, component properties or surface morphology, and are economical substitutes for complete chemical products.

General Information			
Features	General		
Uses	Industrial application		
	Architectural application field		
	Application in Automobile Field		
	General		
	Consumer goods application field		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.2	%	ASTM D955
Water Absorption (24 hr, 3.18 mm)	1.6	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	77.9	MPa	ASTM D638
Tensile Elongation ² (Break)	80	%	ASTM D638
Flexural Modulus	2690	MPa	ASTM D790
Flexural Strength	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	64	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 3.18mm	150	°C	ASTM D648
1.8 MPa, unannealed, 3.18mm	60.0	°C	ASTM D648
Melting Temperature	215	°C	ASTM D789
Additional Information			
模制试验条:模制时干燥			
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	

Mold Temperature	48.9 - 93.3	°C
NOTE		
1.	Type 1, 5.1 mm/min	
2.	Type 1, 5.1 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

