

Diakon® LG156

Polymethyl Methacrylate Acrylic

Lucite International Inc.

Message:

Diakon® LG156 is a polymethyl methacrylate-acrylic material. This product is available in Europe and is processed by extrusion or injection molding. Diakon® The main characteristics of LG156 are: flame retardant/rated flame.

General Information			
UL YellowCard	E108947-218753		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	15	g/10 min	ISO 1133
Water Absorption (Equilibrium, 23°C, 50% RH)	0.30	%	ISO 62

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	85		ISO 2039-2
Ball Indentation Hardness	175	MPa	ISO 2039-1

Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	75.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.0	%	ISO 527-2
Flexural Modulus	2900	MPa	ISO 178
Flexural Stress	105	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	2.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	18	kJ/m ²	ISO 179/1eU
Notched Izod Impact	1.7	kJ/m ²	ISO 180/1A
Multi-Axial Instrumented Impact Energy	0.300	J	ISO 6603-2

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	91.0	°C	ISO 75-2/B
1.8 MPa, not annealed	88.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	98.0	°C	ISO 306/A
--	93.0	°C	ISO 306/B
CLTE - Flow	7.1E-5	cm/cm/°C	ASTM D696

Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

Glow Wire Ignition Temperature	650	°C	IEC 60695-2-13
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ISO 489
Transmittance	92.0	%	ASTM D1003
Haze	0.40	%	ASTM D1003
Additional Information			

Mold Shrinkage, H 961/30: .4 to .7 %.Craze Resistance (isopropanol), Ineos cantilever test: 30 secs to break.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

