

SLOVAMID® 66 GB 30 GF 20

Polyamide 66

Plastcom

Message:

PA 66 chemically reinforced with 20% glass fibre and with the content of 30 % glass beads. Improved anisotropy of shrinkage. The relation of the anisotropy to the mechanical properties can be changed by the ideal combination of the glass fibre and the glass beads. High surface brightness, low rolling resistance force. Manufacturing of exact parts /mainly in flat form/, throttle valves in air piping. Increased strength and tension modulus in tension due to the addition of glass fibre. Delivered in the full RAL colour scale.

General Information			
Filler / Reinforcement	Glass Bead,30% Filler by Weight		
	Glass Fiber,20% Filler by Weight		
Features	Chemically Coupled		
	Good Stiffness		
	Good Strength		
	High Gloss		
Appearance	Colors Available		
	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PA 66		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (275°C/0.325 kg)	1.0	g/10 min	ISO 1133
Molding Shrinkage			STM 64 0808
Across Flow	0.63	%	
Flow	0.56	%	
Water Content	0.15	%	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7800	MPa	ISO 527-2
Tensile Stress (Yield)	150	MPa	ISO 527-2
Tensile Strain (Yield)	3.5	%	ISO 527-2
Flexural Modulus	6580	MPa	ISO 178
Flexural Stress	195	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	7.0	kJ/m ²	
23°C	7.0	kJ/m ²	

Charpy Unnotched Impact Strength			ISO 179
-20°C	45	kJ/m ²	
23°C	55	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	245	°C	ISO 75-2/B
Vicat Softening Temperature	240	°C	ISO 306/B
Melting Temperature (DSC)	260	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+17	ohms·cm	IEC 60093
Electric Strength	40	kV/mm	IEC 60243-1
Comparative Tracking Index	450	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Glow Wire Ignition Temperature	650	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	260 to 290	°C	
Mold Temperature	70.0 to 90.0	°C	
Injection Pressure	70.0 to 120	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

