

TEREZ PA 6 7510 GF 30

Polyamide 6
TER HELL PLASTIC GMBH

Message:
Medium viscosity polyamide 6 with 30% glass fibre reinforcement.
For moulding parts with high rigidity and good impact strength.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Impact Resistance		
	High Stiffness		
	Medium Viscosity		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.35	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9000	MPa	ISO 527-2
Tensile Stress (Break)	165	MPa	ISO 527-2
Tensile Strain (Break)	2.9	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	80	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	215	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT