

Ravago Compounds HM-304 (Comp)

Medium Density Polyethylene

Ravago Manufacturing Americas, LLC

Message:

Key Features:

Excellent long term outdoor weatherability (UV8)

Balance of toughness and rigidity

Excellent low temperature impact

Excellent environmental stress crack resistance, ESCR

Compounded for uniform additive dispersion

Standard, custom or special effect colors available

Excellent opacity available in colors

Standard, custom and natural colors available.

Stock colors may be available. See Stock color bulletin

UL component recognition listing (E141240)

Also available in powder form as HMP-304

General Information			
Features	Good Stiffness		
	Good Toughness		
	Good Weather Resistance		
	High ESCR (Stress Crack Resist.)		
	High Rigidity		
	Low Temperature Impact Resistance		
UL File Number	E141240		
Appearance	Colors Available		
	Natural Color		
	Opaque		
Forms	Pellets		
Processing Method	Compression Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.939	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (100% Igepal, Compression Molded, F50)	1000	hr	ASTM D1693B
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Compression Molded)	17.9	MPa	ASTM D638
Tensile Elongation (Break, Compression Molded)	400	%	ASTM D638
Flexural Modulus - Tangent (Compression Molded)	862	MPa	ASTM D790

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, Compression Molded	63.0	°C	
1.8 MPa, Unannealed, Compression Molded	40.0	°C	
Flammability	Nominal Value	Unit	Test Method
Burning Rate	26	mm/min	ASTM D635
Flame Rating			UL 94
1.52 mm	HB		
3.05 mm	HB		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

