# GECET™ F-200

### Expanded Polystyrene

Fagerdala USA Inc.

#### Message:

GECET TM resins are light weight, and high strength expandable interpolymers that withstand high temperatures. These resins are used in the automotive, bicycle helmet, and other industries where it is required to manage the impact energy. For the same stiffness, a part made from GECET TM resins is 20% and 40% lighter than EPP and PU Foam respectively. Usually a part with the same stiffness made from GECET TM resins costs less than EPP and PU foam part. GECET TM resins parts can be molded for a density range of 2.25 to 20.00 pounds per cubic foot (pcf) enabling the designer to custom-tailor GECET TM resins to specific applications. GECET TM resins may be used for applications that require an end use temperature up to 2500 F. All GECET TM resins are black and micro-pelletized with a particle size of 0.6 - 1.2 mm prior to pre-expansion.

General Information			
Features	Expandable		
	High Heat Resistance		
	High Stiffness		
	High Strength		
Uses	Automotive Applications		
	Safety Helmets		
Appearance	Black		
Forms	Pellets		
Mechanical	Nominal Value	Unit	Test Method
Flexural Strength			ASTM C203
1	2.04	MPa	
<sup>2</sup>	0.945	MPa	
Compressive Strength			ASTM D1621
10% Strain <sup>3</sup>	0.979	MPa	
10% Strain <sup>4</sup>	0.441	MPa	
15% Strain <sup>5</sup>	1.07	MPa	
15% Strain <sup>6</sup>	0.483	MPa	
20% Strain <sup>7</sup>	1.14	MPa	
20% Strain <sup>8</sup>	0.517	MPa	
Flammability	Nominal Value		Test Method
Flame Rating	HBF		UL 94
Flammability - MVSS			FMVSS 302
9	Pass		
10	Pass		
Thermal Resistance - R-Value			ASTM C518
2.54 cm <sup>11</sup>	3.30		
2.54 cm <sup>12</sup>	3.40		
NOTE			

1.	6 lbs/ft <sup>3</sup>
2.	3.5 lbs/ft <sup>3</sup>
3.	6 lbs/ft <sup>3</sup>
4.	3.5 lbs/ft <sup>3</sup>
5.	6 lbs/ft <sup>3</sup>
6.	3.5 lbs/ft <sup>3</sup>
7.	6 lbs/ft <sup>3</sup>
8.	3.5 lbs/ft <sup>3</sup>
9.	3.5 lbs/ft <sup>3</sup>
10.	6 lbs/ft <sup>3</sup>
11.	3.5 lbs/ft <sup>3</sup>
12.	6 lbs/ft <sup>3</sup>

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

