NuSil MED-6342

Silicone

NuSil Technology

Message:

NuSil Technology's restricted materials may be considered for use in short-term implant applications, 29 days or less, or for external applications. A silicone gel is an unreinforced, loosely crosslinked network of polymers. Due to the lack of reinforcing filler, gels tend to be low in viscosity in the uncured state, allowing flexibility for various processing techniques. Not only can the crosslink density of the silicone polymers be designed to yield a very firm or soft gel, but the work time and cure profile can also be modified. Accordingly, gels can be used in a variety of applications, including sheeting and encapsulating sensors or electronic devices. Additionally, NuSil's restricted tacky gels can be used as temporary adhesives. Comments: LOW PENETRATION, HIGH TACK GEL

General Information			
Features	Biocompatible		
	Breathable		
	Low Viscosity		
Uses	Adhesives		
	Electrical/Electronic Applications		
	Medical/Healthcare Applications		
Agency Ratings	USP Class VI Gel		
Forms	Gel		
Processing Method	Encapsulating		
Thermoset	Nominal Value	Unit	
Thermoset Components			
Part A	Mix Ratio by Weight: 1.0		
Part B	Mix Ratio by Weight: 1.0		
Additional Information	Nominal Value	Unit	
Cure System	Platinum		
Penetration Depth ¹	1.25	mm	
Uncured Properties	Nominal Value	Unit	
Viscosity	8.0	Pa·s	
Curing Time (135°C)	0.75	hr	
Pot Life (25°C)	600	min	
NOTE			
	Shaft Weight/Foot Diameter/Time :		
1.	19.5g/6.35mm/5s		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

