

# Ducaseal Static

Flexible Polyvinyl Chloride

Dugdale Plc

## Message:

Ducaseal, PVC compounds have been specially developed for ease of processing on co-extrusion and post co-extrusion processes and are suitable for static and dynamic applications. They enable processors to manufacture end products that will adhere to PVC and offer consistently good surface finish - an important characteristic that minimises the ingress of dust and dirt and adds value by increasing product service life.

Several tailored grades have been produced, all of which offer attractive cost performance ratios.

With a deflection recovery of 25% minimum Ducaseal Static provides a durable seal between PVC profiles and sealed glazing units. Conversely, Ducaseal Dynamic features a deflection recovery of 40% minimum and is designed to offer weatherproof door and window closure seals.

For applications involving contact with PC (polycarbonate), such as conservatory roofing seals, Ducaseal Non-Migratory overcomes the problem of stress cracking.

Ducaseal Anti-Microbial helps to control bacterial growth in damp and humid conditions, for example in showers and bathrooms.

All our compounds are highly specified and meet the performance requirements of BPF 345/2 - PVC-U materials for gaskets and weatherstrips for windows, doors, conservatories and curtain walling.

Materials are available in a range of colours alongside black, white or grey - the most popular shades in Europe.

General Information	
Features	Good Adhesion
	Good Processability
	Good Surface Finish
	Good UV Resistance
Uses	Automotive Applications
	Cable Jacketing
	Gaskets
	Sealing Devices
Appearance	Black
	Colors Available
	White
Forms	Pellets
Processing Method	Coextrusion
	Extrusion

Physical	Nominal Value	Unit
Specific Gravity	1.20 to 1.40	g/cm <sup>3</sup>
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A)	50 to 90	
Mechanical	Nominal Value	Unit
Tensile Strength	> 10.0	MPa
Tensile Elongation (Break)	250 to 500	%
Thermal	Nominal Value	Unit

Service Temperature	-10 to 70	°C
Deflection Recovery - 14 days (55°C)	> 25.0	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT