

AKROMID® T1 GF 30 9 black (3498)

Polyphthalamide
AKRO-PLASTIC GmbH

Message:

AKROMID® T1 GF 30 9 black (3498) is a 30% glass fibre reinforced, process improved polyphthalamide with high rigidity and strength, as well as high temperature and chemical resistance
Applications are parts with tight dimensional tolerances even under high mechanical load.

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Features		Good Chemical Resistance		
		Good Dimensional Stability		
		High Heat Resistance		
		High Rigidity		
		High Strength		
Appearance		Black		
Resin ID (ISO 1043)		PPA GF30		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.42	--	g/cm ³	ISO 1183
Humidity Absorption - 62% RH (70°C)	1.3	--	%	ISO 1110
Flexural Strain at Break ¹	3.0	--	%	ISO 178
Temperature Index				IEC 216
50% Loss of Tensile Strength, 20000 hr	130 to 140	--	°C	
50% Loss of Tensile Strength, 5000 hr	150 to 160	--	°C	
Reinforcement Content	30	--	%	ISO 1172
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 961/30)	270	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	12000	12000	MPa	ISO 527-2/1
Tensile Stress (Break)	210	190	MPa	ISO 527-2/5
Tensile Strain (Break)	2.3	2.3	%	ISO 527-2/5
Flexural Modulus ²	11000	--	MPa	ISO 178
Flexural Stress ³	300	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	45	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	50	--	kJ/m ²	ISO 179/1eU

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
1.8 MPa, Unannealed	275	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	165	--	°C	ISO 75-2/C
Melting Temperature ⁴	308	--	°C	DIN EN 11357-1
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate ⁵ (1.00 mm)	< 100	--	mm/min	FMVSS 302
Flame Rating (0.800 mm)	HB	--		UL 94
NOTE				
1.	2 mm/min			
2.	2.0 mm/min			
3.	2.0 mm/min			
4.	10 K/min, DSC			
5.	> 1 mm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

