

TOTAL Polyethylene LDPE FE 8000

Low Density Polyethylene
TOTAL Refining & Chemicals

Message:

LDPE FE 8000 is a low density polyethylene produced by a high pressure autoclave process. This grade is particularly suitable for transparent thin film. LDPE FE 8000 is suited to many applications in the field of consumer, industrial, food or hygiene packaging such as collation shrink, lamination and coextrusion film.

General Information			
Uses	Packaging		
	Films		
	Laminate		
	Industrial application		
	Food packaging		
	Shrinkable film		
	Consumer goods application field		
Agency Ratings	EC 1907/2006 (REACH)		
Forms	Particle		
Processing Method	Blow film		
	Co-extrusion molding		
Multi-Point Data	Specific Volume vs Temperature (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density			
--	0.924	g/cm³	ISO 1183
--	924	kg/m³	ISO 1183 ¹
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.80	g/10 min	ISO 1133
Melt volume-flow rate (190°C/2.16 kg)	1.00	cm³/10min	ISO 1133 ²
Water Absorption (Saturation)	0.010	%	ISO 62 ³
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	240	MPa	ISO 527-2 ⁴
Tensile Stress (Yield)	12.0	MPa	ISO 527-2 ⁵
Tensile Strain (Yield)	15	%	ISO 527-2 ⁶
Tensile Elongation at Break	> 50	%	ISO 527-2 ⁷
Films	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-3
MD: Yield, 40 µm, blown film	12.0	MPa	ISO 527-3
TD: Yield, 40 µm, blown film	12.0	MPa	ISO 527-3
MD: Broken, 40 µm, blown film	27.0	MPa	ISO 527-3

TD: Broken, 40 µm, blown film	23.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Broken, 40 µm, blown film	370	%	ISO 527-3
TD: Broken, 40 µm, blown film	570	%	ISO 527-3
Dart Drop Impact (40 µm, Blown Film)	120	g	ISO 7765-1
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa)	41.0	°C	ISO 75-2 ⁸
Vicat Softening Temperature			
--	99.0	°C	ISO 306
50°C/h, B (50N)	98.0	°C	ISO 306 ⁹
Melting Temperature (DSC)			
--	111	°C	ISO 3146
-- ¹⁰	114	°C	ISO 11357-3 ¹¹
CLTE - Flow	1.8E-4	cm/cm/°C	ISO 11359-2 ¹²
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093 ¹³
Volume Resistivity	> 1.0E+13	ohms·m	IEC 60093 ¹⁴
Relative Permittivity (100 Hz)	2.00		IEC 60250 ¹⁵
Dissipation Factor			IEC 60250 ¹⁶
100 Hz	2.0E-4		IEC 60250
1 MHz	2.0E-4		IEC 60250
Comparative Tracking Index	600		IEC 60112 ¹⁷
Flammability	Nominal Value	Unit	Test Method
Burning Behav. at 1.6mm nom. thickn. (1.60 mm)	HB		ISO 1210 ¹⁸
Oxygen Index	18	%	ISO 4589-2 ¹⁹
Additional Information			
The value listed as Melting Temperature, ISO 3146, was tested in accordance with ISO 11357. Elmendorf, ISO 6383-2, MD, Blown Film, 40 µm: 53 N/mm Elmendorf, ISO 6383-2, TD, Blown Film, 40 µm: 47 N/mm Haze, ISO 14782, Blown Film, 40 µm: 11%			
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	160 - 200	°C	
Cylinder Zone 2 Temp.	160 - 200	°C	
Cylinder Zone 3 Temp.	160 - 200	°C	
Cylinder Zone 4 Temp.	160 - 200	°C	
Cylinder Zone 5 Temp.	160 - 200	°C	
NOTE			
1.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???		
2.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???		
3.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???		
4.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???		

5.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
6.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
7.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
8.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
9.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
10.	10 °C/min
11.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
12.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
13.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
14.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
15.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
16.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
17.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
18.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???
19.	?????,?? ISO 10350 ??? 23°C/50%r.h. ???

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT