## MORETEC<sup>™</sup> 0218VN

## Linear Low Density Polyethylene

Prime Polymer Co., Ltd.

## Message:

MORETEC<sup>™</sup>0218VN is a linear low density polyethylene product. It can be processed by casting film and is available in North America, Europe or Asia Pacific. MORETEC<sup>™</sup>The application areas of 0218VN include film and coating applications. The main characteristics are: good sealing performance.

General Information			
Features	Low temperature heat sealability	1	
Uses	Films		
	Laminate		
Forms	Particle		
Processing Method	cast film		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	2.1	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance	1000		
(Injection Molded)	> 1000	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, Injection	52		
Molded)	52		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, Injection Molded)	7.70	MPa	ISO 527-2
Tensile Strain (Break, Injection Molded)	300	%	ISO 527-2
Flexural Modulus (Injection Molded)	140	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength			
(Injection Molded)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	90.0	°C	ISO 306
Melting Temperature (DSC)	117	°C	ISO 3146
Additional Information			

The value listed as Melting Temperature, ISO 3146, was tested in accordance with ISO 11357-3Tensile Strain at Break, ISO 527: >300%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

