

# Matrixx TPP2B40

Polypropylene Copolymer

The Matrixx Group, Inc.

## Message:

Matrixx TPP2B40 is a polypropylene copolymer (PP Copoly) material, which contains 40% talc filler. This product is available in North America and is processed by injection molding.

The main features of the Matrixx TPP2B40 are:

flame retardant/rated flame

Copolymer

General Information			
Filler / Reinforcement	Talc filler, 40% filler by weight		
Features	Copolymer		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 - 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	23.4	MPa	ASTM D638
Flexural Modulus - Tangent	2620	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	48	J/m	ASTM D256
Dart Drop Impact	5.08	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	127	°C	ASTM D648
1.8 MPa, not annealed	73.9	°C	ASTM D648
RTI	65.6	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2 - 104	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	177 - 221	°C	
Middle Temperature	177 - 221	°C	
Front Temperature	177 - 221	°C	
Processing (Melt) Temp	199 - 227	°C	
Mold Temperature	21.1 - 48.9	°C	
Injection Rate	Moderate		

Back Pressure	0.138 - 2.07	MPa
Cushion	6.35 - 12.7	mm
Injection instructions		

Drying not normally required Injection Booster Pressure: Maximum without flash, 60% of machine maximum, target Screw Speed: Slow to Medium

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

