

# Sylvin 5143-88 White 1593

Polyvinyl Chloride  
Sylvin Technologies Incorporated

Message:

Sylvin 5143-88 White 1593 Is A RoHS Compliant Vinyl Compound Formulated For Wire Insulating And Outdoor Jacketing Applications. This Compound Has A Underwriters Laboratories Approval For TW Type Wire And 720 Hour Sunlight Resistance.

General Information			
Uses	Cable sheath		
	Wire and cable applications		
	Insulating material		
	Outdoor application		
Wire Types	TW		
RoHS Compliance	RoHS compliance		
Appearance	White		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	84		ASTM D2240
Shaw A, 10 seconds	84		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	14.5	MPa	ASTM D638
Tensile Elongation (Break)	380	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	75.0	°C	ASTM D794
Brittleness Temperature	-24.0	°C	ASTM D746
Melting Temperature	168 - 179	°C	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	27	%	ASTM D2863
Flammability	VW-1		UL 1581

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

