## Desmoderm® KCW

Polyurethane (Polyester based)

Covestro - PUR

## Message:

Desmoderm KCW Granular is a one-component polyester polycarbonate urethane based on an aromatic diisocyanate.

| General Information                |                                  |      |                     |
|------------------------------------|----------------------------------|------|---------------------|
| Features                           | Hydrolysis Resistant             |      |                     |
|                                    | Soft                             |      |                     |
|                                    |                                  |      |                     |
| Forms                              | Granules                         |      |                     |
| Physical                           | Nominal Value                    | Unit | Test Method         |
| Viscosity <sup>1</sup>             |                                  |      | DIN EN ISO 3219/A.3 |
| Tempered 5 hr, 120°C : 23°C        | 4.00 to 50.0                     | Pa·s |                     |
| Untempered : 23°C                  | 4.00 to 20.0                     | Pa·s |                     |
| Light-Fastness                     | 3.00                             |      | DIN EN ISO 105-B02  |
| Softening Range                    | 170 to 180                       | °C   |                     |
| Films                              | Nominal Value                    | Unit | Test Method         |
| Film Thickness - Tested            | 100                              | μm   |                     |
| Tensile Modulus - 100% (100 μm)    | 6.00 to 7.00                     | МРа  | DIN 53504           |
| Tensile Strength                   |                                  |      | DIN 53504           |
| 100 μm                             | 40.0 to 50.0                     | МРа  |                     |
| 70°C, 100 μm <sup>2</sup>          | 38.0 to 48.0                     | МРа  |                     |
| Tensile Elongation (Break, 100 µm) | 350 to 450                       | %    | DIN 53504           |
| NOTE                               |                                  |      |                     |
|                                    | 20% solution in                  |      |                     |
| 1.                                 | dimethylformamide                |      |                     |
| 2.                                 | after 14 days hydrolysis, 95% RH |      |                     |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

