

NILAMID® XS3 GF55 TF10

Polyamide
Nilit Plastics

Message:

SPECIALTY PARTIALLY AROMATIC POLYAMIDE BLEND
DEVELOPED AS ALTERNATIVE TO METAL
GOOD STIFFNESS AND TENSILE STRENGTH
VERY LOW WARPAGE
VERY GOOD CREEP RESISTANCE
EXCELLENT SURFACE QUALITY
HIGH DIMENSIONAL STABILITY
PERFORMANCE INDEPENDENT FROM ENVIRONMENTAL CONDITIONS
PARTIALLY AROMATIC PA, 55% GLASS FIBER REINFORCED, 10% PTFE LUBRICATED

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 55% filler by weight		
Additive		PTFE lubricant (10%)		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.73	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Transverse flow: 23°C	0.30	--	%	ISO 294-4
Flow: 23°C	0.070	--	%	ISO 294-4
Water Absorption				ISO 62
23°C, 24 hr	0.50	--	%	ISO 62
Saturated, 23°C	3.5	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	19000	17500	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	190	170	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.5	2.7	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60	--	kJ/m ²	ISO 179/1eU
23°C	66	60	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)				ISO 180/A
	12	13	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature ¹ (1.8 MPa, Unannealed)				
	235	--	°C	ISO 75-2/A
Continuous Use Temperature ²				
	120	--	°C	IEC 60216
Electrical	Dry	Conditioned	Unit	Test Method

Comparative Tracking Index (3.20 mm, Solution A)				
	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.40 mm	HB	--		UL 94
0.8 mm	HB	--		UL 94
1.6 mm	HB	--		UL 94
3.2 mm	HB	--		UL 94
NOTE				
1.	Method B			
2.	2000 hr			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT