

# Softell TKG 259N G21385

Polypropylene Copolymer

LyondellBasell Industries

Message:

Softell TKG 259N G21385 is a glass fiber reinforced PP copolymer, with high stiffness, excellent scratch resistance, superior dimensional stability and low gloss. The product is also available as a customized color matched, pellet form. This grade is delivered in G21385 color version. For regulatory compliance information, see Softell TKG 259N G21385 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS). This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Features	Good dimensional stability		
	Rigidity, high		
	Copolymer		
	Gloss, low		
	Workability, good		
	Scratch resistance		
Uses	Soft		
Appearance	Application in Automobile Field		
	Car interior equipment		
Forms	Available colors		
	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.04	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus <sup>1</sup> (23°C)	1700	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (-30°C)	7.0	kJ/m²	ISO 180/1A
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

