

RTV-2 XT-386/400

Silicone

Silicones, Inc.

Message:

XT-386 is a variation of GI-311 Base. In this formulation, the crosslinker has been added to the Base to enable rapid curing via the addition of tin catalyst.
Appearance: White to bluff color. Mild sweet odor.

General Information		
Features	Fast Cure	
Uncured Properties	Nominal Value	Unit
Color	White	
Viscosity ¹	8.0 to 12	Pa·s
Curing Time	2.0	hr
Pot Life	35	min
Cured Properties	Nominal Value	Unit
Shore Hardness		
Shore A ²	5	
Shore A ³	30	
NOTE		
1.	Base	
2.	After 2 Hours	
3.	After 4 Hours	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT