

# UPES® IP-73-UHP

Polystyrene + PE

NOVA Chemicals

## Message:

UPES® IP-73-UHP is a Polystyrene + PE (PS+PE) material. It is available in North America.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm <sup>3</sup>	ASTM D6226
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	< 0.10	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup> (Injection Molded)	1900	MPa	ASTM D638
Tensile Strength <sup>2</sup> (Break, Injection Molded)	24.8	MPa	ASTM D638
Tensile Elongation <sup>3</sup> (Break, Injection Molded)	120	%	ASTM D638
Flexural Modulus (Injection Molded)	1740	MPa	ASTM D790
Flexural Strength <sup>4</sup> (Yield, Injection Molded)	51.7	MPa	ASTM D790
Flexural Strain - Yield <sup>5</sup>	> 5.0	%	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Injection Molded)	43	J/m	ASTM D256
Unnotched Izod Impact (Injection Molded)	340	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	81.4	°C	ASTM D1525 <sup>6</sup>
NOTE			
1.	5.1 mm/min		
2.	5.1 mm/min		
3.	5.1 mm/min		
4.	1.3 mm/min		
5.	0.05 in/min, Injection Molded		
6.	Rate B (120°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

