

VALOX™ VC108 resin

Polybutylene Terephthalate
SABIC Innovative Plastics Asia Pacific

Message:

VALOX™ VC108 resin is a Polybutylene Terephthalate (PBT) material. It is available in Asia Pacific.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm³	ASTM D792
Molding Shrinkage - Flow			Internal Method
3.20 mm	0.30 to 0.50	%	
6.40 mm	0.80 to 1.0	%	
Water Absorption (24 hr)	0.070	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	98.1	MPa	Internal Method
Tensile Elongation (Break)	3.0	%	Internal Method
Flexural Modulus	5980	MPa	ASTM D790
Flexural Strength	148	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	39	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.20 mm)	199	°C	ASTM D648
CLTE - Flow (-30 to 30°C)	8.0E-5	cm/cm/°C	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+8 to 1.0E+12	ohms	ASTM D257

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT