

# Bergamid™ B70 GK/MI15 black

Polyamide 6

PolyOne Corporation

Message:

6016158

General Information			
Filler / Reinforcement	Glass Bead\Mineral,15% Filler by Weight		
Features	Good Dimensional Stability		
	Good Impact Resistance		
	Good Stiffness		
	Good UV Resistance		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity <sup>1</sup>	1.24	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage - Flow <sup>2</sup> (23°C, 4.00 mm, Injection Molded)	1.5 to 2.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C, 4.00 mm, Injection Molded)	4400	MPa	ISO 527-2/1
Tensile Strength <sup>3</sup> (23°C, 4.00 mm, Injection Molded)	73.0	MPa	ISO 527
Tensile Strain (Break, 23°C, 4.00 mm, Injection Molded)	3.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.6	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C, Injection Molded)	50	kJ/m <sup>2</sup>	ISO 179
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.20 mm, ALL)	HB		Internal Method
Glow Wire Flammability Index (3.00 mm)	750	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	240 to 280	°C	

Mold Temperature	65.0 to 85.0	°C
NOTE		
1.	±0.03	
2.	Bergmann Method	
3.	5.0 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

