

# Manner Flexible PVC X3563

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

## Message:

Lead-free profile extrusion compound suitable for dual extrusion with rigid PVC. This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

General Information	
Features	Low (to None) Lead Content
Uses	Profiles
RoHS Compliance	RoHS Compliant
Processing Method	Coextrusion Profile Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38 to 1.42	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	76		
Shore A, 15 sec	70		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
0.762 mm	13.4	MPa	
100% Strain,0.762 mm	5.17	MPa	
Tensile Elongation (Break, 0.762 mm)	380	%	ASTM D638

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

