

LEXAN™ 1278R resin

Polycarbonate

SABIC Innovative Plastics Europe

Message:

LEXAN 1278R is a medium viscosity, 20% glass reinforced, flame retardant grade, offering a very high rigidity. It is especially designed for applications like industrial enclosures and fuse boxes requiring a low knock-out strength for moulded-in membranes.

General Information			
UL YellowCard	E45329-236640	E45329-236641	
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Flame Retardant		
	High Rigidity		
	Medium Viscosity		
Uses	Industrial Applications		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.35	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	12.0	cm³/10min	ISO 1133
Molding Shrinkage - Flow ¹	0.20 to 0.50	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.29	%	
Equilibrium, 23°C, 50% RH	0.12	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	160	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5200	MPa	ISO 527-2/1
Tensile Stress (Break)	80.0	MPa	ISO 527-2/5
Tensile Strain (Break)	2.0	%	ISO 527-2/5
Flexural Modulus ²	5000	MPa	ISO 178
Flexural Stress	120	MPa	ISO 178
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	17.0	mg	Internal Method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
-30°C ³	5.0	kJ/m²	ISO 179/1eA
-20°C	5.0	kJ/m²	ISO 179/2C
23°C ⁴	6.0	kJ/m²	ISO 179/1eA
23°C	8.0	kJ/m²	ISO 179/2C

Charpy Unnotched Impact Strength			
-30°C ⁵	40	kJ/m ²	ISO 179/1eU
-30°C	5.0	kJ/m ²	ISO 179/2U
23°C ⁶	40	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength ⁷			ISO 180/1A
-30°C	6.0	kJ/m ²	
23°C	7.0	kJ/m ²	
Unnotched Izod Impact Strength ⁸			ISO 180/1U
-30°C	35	kJ/m ²	
23°C	35	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁹			
0.45 MPa, Unannealed, 100 mm Span	140	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 100 mm Span	134	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	151	°C	ISO 306/A50
--	141	°C	ISO 306/B50
--	143	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE - Flow (23 to 80°C)	3.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.22	W/m/K	ISO 8302
RTI Elec	120	°C	UL 746
RTI Imp	120	°C	UL 746
RTI Str	120	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Electric Strength (3.20 mm, in Oil)	16	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
50 Hz	3.00		
60 Hz	3.00		
1 MHz	2.90		
Dissipation Factor			IEC 60250
50 Hz	1.0E-3		
60 Hz	1.0E-3		
1 MHz	0.010		
Comparative Tracking Index			IEC 60112
--	150	V	
Solution B	125	V	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-1		UL 94
Glow Wire Flammability Index			IEC 60695-2-12

1.00 mm	850	°C	
3.20 mm	960	°C	
Oxygen Index	34	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 to 80.0	°C	
Rear Temperature	260 to 280	°C	
Middle Temperature	270 to 290	°C	
Front Temperature	280 to 310	°C	
Nozzle Temperature	270 to 290	°C	
Processing (Melt) Temp	280 to 310	°C	
Mold Temperature	80.0 to 110	°C	

NOTE		
1.	Tensile Bar	
2.	2.0 mm/min	
3.	80*10*3 sp=62mm	
4.	80*10*3 sp=62mm	
5.	80*10*3 sp=62mm	
6.	80*10*3 sp=62mm	
7.	80*10*3	
8.	80*10*3	
9.	120*10*4 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

