

Soarnol® D2908

Ethylene Vinyl Alcohol

Soarus L.L.C.

Message:

Soarnol D2908 is a 29 mol% ethylene content standard grade of Soarnol with an intermediate melt flow rate. Soarnol D2908 has excellent gas barrier property at low humidity and is primarily used in coextruded sheet and coextrusion coating applications. This resin can also be used in coextruded film and coextruded blow-molded containers.

General Information			
Features	Copolymer		
	Medium liquidity		
	Gas barrier property		
	Compliance of Food Exposure		
Uses	Blown Containers		
	Films		
	Sheet		
	Coating application		
Agency Ratings	EU 90/128/EEC		
	FDA 21 CFR 177.1360		
Forms	Particle		
Processing Method	Blow molding		
	Co-extruded film		
	Co-extrusion molding		
	Extrusion		
	Coating		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (210°C/2.16 kg)	8.0	g/10 min	
Ethylene Content	29.0	wt%	Internal method
Volatile Matter		%	
Films	Nominal Value	Unit	Test Method
Oxygen Permeability ¹ (20°C, 20 µm)	0.400	cm ³ /m ² /24 hr	Internal method
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	62.0	°C	DSC
Melting Temperature	188	°C	DSC
Peak Crystallization Temperature (DSC)	163	°C	DSC
Extrusion	Nominal Value	Unit	

Cylinder Zone 1 Temp.	180	°C
Cylinder Zone 2 Temp.	200	°C
Cylinder Zone 3 Temp.	220	°C
Cylinder Zone 4 Temp.	230	°C
Cylinder Zone 5 Temp.	230	°C
Adapter Temperature	230	°C

Extrusion instructions

Extruder: 40 mm Single screw extruder, L/D = 28Screw: Full-flighted, constant pitch type, CR = 3.5Screen pack: 80/120/50 meshDie: Manifold type, die width = 450 mm, lip clearance = 0.2 mm

NOTE

1.
- Measured with OXTRAN 10/50
(MOCON), 65%RH

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT