

POLYVIN® Polyvin SNP 0501-

Polyvinyl Chloride

A. Schulman Inc.

Message:

Flexible PVC extrusion formulation used for profiles requiring ease of processing, excellent anti-itch & squeak and a non-"Class A" show surface. GM-7001M callout (low CoF). Can be co-extruded with flexible PVCs to replace GBIE coating.

General Information			
Processing Method	Profile extrusion molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	69		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2.01	MPa	ASTM D638
Tensile Strength ² (Yield)	2.60	MPa	ASTM D638
Tensile Elongation ³ (Break)	150	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Compression Set (70°C, 22 hr)	0.0	%	ASTM D395
NOTE			
1.	Type 4,500mm/min		
2.	Type 4,500mm/min		
3.	Type 4,500mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

