

UBE Nylon 5034 FDX17

Polyamide 66/6 Copolymer
UBE Engineering Plastics, S.A.

Message:

UBE NYLON 5034 FDX17 is a high viscosity Polyamide 6/6.6 copolymer containing an anti block agent. The material is especially suitable as outer layer for air-cooled blown film (asymmetric layer structure). Typical applications are for pouches and thermoformed products.

General Information			
Additive	Anti-caking agent		
Features	Anti-caking property		
	Workability, good		
	Definition, high		
	Compliance of Food Exposure		
	High shrinkage		
	Viscosity, High		
Uses	Films		
Agency Ratings	European food contact, not rated		
Forms	Particle		
Processing Method	Blow film		
	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ASTM D1894
With self-dynamics	0.30		ASTM D1894
With Self-Static	0.30		ASTM D1894
Films	Nominal Value	Unit	Test Method
Secant Modulus - MD (Cast Film)	550	MPa	ASTM D882
Tensile Strength - MD			ASTM D882
Yield, extruded film	27.0	MPa	ASTM D882
Fracture, extruded film	115	MPa	ASTM D882
Tensile Elongation - MD (Fracture, Extruded Film)	650	%	ASTM D882
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	197	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257
Optical	Nominal Value	Unit	Test Method
Gardner Gloss	140		ASTM D523

Haze	3.5	%	ASTM D1003
------	-----	---	------------

Additional Information

The value listed as Melting Temperature, ISO 3146, was tested in accordance with ISO 11357. The value listed as Surface Resistivity, ASTM D257, was tested in accordance with UBE test methods. Oxygen Permeability, ASTM D3985: 37 ml/m²/day Relative Viscosity, JIS K6810, 96% H₂SO₄, conc. 1.0 g/100 ml: 4.09 Extractable Content, JIS K6810: <1.0 wt% Molecular Ratio, PA6/PA6.6: 80/20 Water Vapor Permeability, JIS Z0208: 90 g/m²/day Piercing Strength, JAS P1019, Cast Film: 9.5 N Piercing Elongation, JAS P1019, Cast Film: 15 mm Flex Crack Resistance, MIL B131B, 23°C, 1000 cycle, Cast Film: <10 hole/0.04 m² Gelbo Test, MIL B131B, 5°C, 100 cycle, Cast Film: <10 hole/0.04 m²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

