

Veroplas 660

Acrylonitrile Butadiene Styrene

PlastxWorld Inc.

Message:

Veroplas 660 is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in Europe or North America. Characteristics include:

- Flame Rated
- High Flow
- Impact Resistant

General Information			
UL YellowCard	E315545-100118257		
Features	General Purpose		
	High Flow		
	Medium Impact Resistance		
Uses	General Purpose		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	44.1	MPa	ASTM D638
Flexural Modulus	2340	MPa	ASTM D790
Flexural Strength	68.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	170	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 12.7 mm)	87.2	°C	ASTM D648
Vicat Softening Temperature	92.8	°C	ASTM D1525 ¹
CLTE - Flow	9.0E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm, ALL)	HB	UL 94	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

