# Braskem PP TI2900C

### High Crystallinity Polypropylene

#### Braskem America Inc.

#### Message:

Sub-group High Crystallinity Copolymer Description Highly crystalline homopolymer phase, very high molecular weight EPR phase, very high flexural modulus, reduced emissions, reduced gels, high melt flow Applications Suggested uses include compounding

| General Information  |                             |          |             |
|--|-----------------------------|----------|-------------|
| Features   | Copolymer                   |          |             |
|  | Food Contact Acceptable     |          |             |
|  | Highly Crystalline          |          |             |
|  | Low Emissions               |          |             |
|  | Low Gel                     |          |             |
|  | Ultra High Molecular Weight |          |             |
| Uses   | Compounding                 |          |             |
| Agency Ratings   | FDA 21 CFR 177.1520         |          |             |
| Forms  | Pellets                     |          |             |
| Processing Method  | Compounding                 |          |             |
| Physical   | Nominal Value               | Unit     | Test Method |
| Melt Mass-Flow Rate (MFR) (230°C/2.16                        |                             |          |             |
| kg)  | 110                         | g/10 min | ASTM D1238  |
| Mechanical   | Nominal Value               | Unit     | Test Method |
| Tensile Strength <sup>1</sup> (Yield, Injection Molded)      | 33.8                        | MPa      | ASTM D638   |
| Tensile Elongation <sup>2</sup> (Yield, Injection<br>Molded) | 5.0                         | %        | ASTM D638   |
| Flexural Modulus - 1% Secant <sup>3</sup> (Injection Molded) | 1590                        | MPa      | ASTM D790A  |
| Impact   | Nominal Value               | Unit     | Test Method |
| Notched Izod Impact (23°C, Injection<br>Molded)              | 37                          | J/m      | ASTM D256A  |
| NOTE   |                             |          |             |
| 1.   | 51 mm/min                   |          |             |
| 2.   | 51 mm/min                   |          |             |
| 3.   | 1.3 mm/min                  |          |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

