

# Beetafin® L9017

Polyurethane (Polyester based)

BIP (Oldbury) Limited

## Message:

An anionic, very soft, flexible, light fast polyester based, aliphatic aqueous polyurethane dispersion.

Characteristics:

- Gives very soft and extremely flexible films
- Supplied as a high solids dispersion
- Good properties as a hot melt adhesive
- Does not discolour on exposure to daylight
- Dried films exhibit tackiness
- Good adhesion to synthetic and natural materials

Applications:

- Leather Finishing
- Plastic Coatings
- Textile Coatings
- Hot melt adhesive
- Textile Finishing
- Printing ink binders

General Information	
Features	Aliphatic
	Good Adhesion
	Good Flexibility
	Soft
Uses	Adhesives
	Coating Applications
	Printing Ink
	Textile Applications

Physical	Nominal Value	Unit	
pH	8.0		
Solids Content	60	%	
Films	Nominal Value	Unit	
Tensile Modulus - 100%	0.500	MPa	
Tensile Strength - MD (Break)	5.00	MPa	
Tensile Elongation - MD (Break)	1600	%	
Uncured Properties	Nominal Value	Unit	Test Method
Viscosity (25°C)	0.50	Pa · s	Brookfield

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

