

HIPOL™ J340

Polypropylene Impact Copolymer

Mitsui Chemicals, Inc.

Message:

HIPOL™ J340 is a Polypropylene Impact Copolymer (PP Impact Copolymer) material. It is available in Asia Pacific for injection molding.

Important attributes of HIPOL™ J340 are:

Flame Rated

Copolymer

Good Processability

Impact Resistant

Typical applications include:

Containers

Engineering/Industrial Parts

General Information			
Features	Block Copolymer		
	Good Impact Resistance		
	Good Moldability		
Uses	Containers		
	Industrial Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.8	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	25.5	MPa	
Break	19.6	MPa	
Tensile Elongation (Break)	500	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	78	J/m	
0°C	120	J/m	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	100	°C	
1.8 MPa, Unannealed	55.0	°C	
Vicat Softening Temperature	150	°C	ASTM D1525

Flammability	Nominal Value	Test Method
Flame Rating (1.57 mm, ALL)	HB	UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

