

Geon™ Vinyl Packaging 2188GC

Rigid Polyvinyl Chloride

PolyOne Corporation

Message:

Geon™ Vinyl Packaging 2188GC is a Rigid Polyvinyl Chloride product. It can be processed by blow molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon™ Vinyl Packaging 2188GC include bottles, food contact applications and packaging.

Characteristics include:

Food Contact Acceptable

High Gloss

Impact Resistant

General Information			
Features	Food Contact Acceptable High Gloss High Impact Resistance		
Uses	Bottles Packaging		
Agency Ratings	FDA Food Contact, Unspecified Rating		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Blow Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.32	g/cm ³	ASTM D792
--	0.801	g/cm ³	ASTM D1505
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Durometer Hardness (Shore D)	79		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2390	MPa	ASTM D638
Tensile Strength ² (Yield)	43.4	MPa	ASTM D638
Flexural Modulus	2580	MPa	ASTM D790
Flexural Strength	77.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	1100	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	59.4	°C	ASTM D648
Optical	Nominal Value	Unit	Test Method

Transmittance		Internal Method
851 μm, 400 nm	81.0	%
851 μm, 700 nm	86.5	%
Additional Information	Nominal Value	Unit
Blow Molding Temperature	202 to 213	°C
NOTE		
1.	Type I, 5.1 mm/min	
2.	Type I, 5.1 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

