MARCOBLEND 1000 BK05

Polycarbonate

POLY GIN

Message:

MARCOBLEND 1000 BK05 is a high gloss polycarbonate resin. The resin is Halogen free and compliance with TCO and RoHS certification. The unique characters include superior processability, good stiffness, and excellent dimension stability and suitable for use in TFT LCD frame and NB battery cover.

| General Information | | | |
|--|----------------------------|----------|-------------|
| Features | Good Dimensional Stability | | |
| | Good Processability | | |
| | Good Stiffness | | |
| | Halogen Free | | |
| | High Gloss | | |
| | | | |
| RoHS Compliance | RoHS Compliant | | |
| Appearance | Black | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.20 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (300°C/1.2 kg) | 24 | g/10 min | ASTM D1238 |
| Molding Shrinkage - Flow | 0.40 to 0.60 | % | ASTM D955 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 70.5 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 90 | % | ASTM D638 |
| Flexural Modulus | 2600 | MPa | ASTM D790 |
| Flexural Strength | 121 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C) | 700 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 | | | |
| MPa, Unannealed) | 121 | °C | ASTM D648 |
| Flammability | Nominal Value | | Test Method |
| Flame Rating | V-0 | | UL 94 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 120 | °C | |
| Drying Time | 3.0 to 4.0 | hr | |
| Rear Temperature | 260 to 265 | °C | |
| Middle Temperature | 265 to 270 | °C | |
| Front Temperature | 270 to 275 | °C | |
| Nozzle Temperature | 275 to 290 | °C | |
| Mold Temperature | 80.0 to 120 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

