

LETOXIT PR 220

Epoxy; Epoxide

5M s.r.o.

Message:

Applications:

for production of laminated segments reinforced with glass, carbon or kevlar fibers

using: parts of airplanes, sailplanes, sport boats, carriage bodies...

Special properties:

extremely liquid low molecular resin without filling material

Type: low molecular epoxy laminated resin

Application method: Mix Letoxit PR 220 with suitable curing agent according to the application method and required final properties of laminates. From production of 5M it is possible to use Letoxit EM 315, EM 316 or EM 317. If the mixture ratio is not stated, it is possible to determine the quantity of curing agent in grams for 100g of epoxy resin:

$x = He \cdot Eekv$

x = quantity of curing agent in grams for 100 grams of epoxy resin

resin:

He = hydrogen equivalent weight of curing agent

Eekv = epoxy equivalent epoxy resin in mol/100 g

General Information		
Features	Low Molecular Weight	
Uses	Aircraft Applications	
	Laminates	
	Water Sports Equipment	
Appearance	Clear/Transparent	
	Yellow	
Forms	Liquid	
Physical	Nominal Value	Unit
Density	1.15 to 1.23	g/cm ³
Solution Viscosity ¹	600 to 900	mPa · s
Thermoset	Nominal Value	Unit
Shelf Life	26	wk
Additional Information	Nominal Value	Unit
Epoxy Equivalent	E(evk) = 0.59 to 0.65	
Storage Temperature	5 to 35	°C
NOTE		
1.	25°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

