

ESTOPLAST EP 1500-E

Polybutylene Terephthalate

Ester Industries Ltd.

Message:

Polybutylene Terephthalate - Unfilled
Electrical & Electronics - High viscosity material suitable for extrusion/injection molding grade.

General Information			
Additive	demoulding		
Features	Good demoulding performance		
	Medium viscosity		
Uses	Electrical/Electronic Applications		
RoHS Compliance	RoHS compliance		
Appearance	Natural color		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Water Absorption			ISO 62
Saturated, 23°C	0.50	%	ISO 62
Equilibrium, 23°C, 50% RH	0.25	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	55.0	MPa	ASTM D638
Tensile Elongation (Break)	> 50	%	ASTM D638
Flexural Strength	85.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	60	J/m	ASTM D256A
Unnotched Izod Impact (23°C)	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	140	°C	ASTM D648
1.8 MPa, not annealed	70.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Comparative Tracking Index	550	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94

0.75 mm	HB	UL 94
1.5 mm	HB	UL 94
Extrusion	Nominal Value	Unit
Drying Temperature	110 - 120	°C
Drying Time	3.0 - 4.0	hr
Hopper Temperature	210 - 220	°C
Cylinder Zone 1 Temp.	240 - 245	°C
Cylinder Zone 2 Temp.	245 - 250	°C
Cylinder Zone 3 Temp.	245 - 250	°C
Cylinder Zone 4 Temp.	250 - 255	°C
Die Temperature	245 - 250	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

