Vital-Line SHM5505

Flexible Polyvinyl Chloride

Teknor Apex Asia Pacific PTE. LTD.

Message:

Vital-Line SHM5505 is a flexible polyvinyl chloride material. This product is available in the Asia-Pacific region and is processed by injection molding. The main characteristics of Vital-Line SHM5505 are: plasticization.

The typical application fields of Vital-Line SHM5505 are: medical/health care

General Information			
Features	Non-phthalate plasticizer		
Uses	Medical/nursing supplies		
Forms	Particles		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20 - 1.24	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	72 - 78		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	> 11.8	MPa	ASTM D638
Tensile Elongation (Break)	370	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Thermal stability-Oven (190°C)	> 30.0	min	ASTM D2115-92

Typical temperature profile for processing compound is from 135°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process. Feeding zone: 135°CMixing zone: 140°C~165°CNozzle/Die zone: 160°C~180°CMould temperature: 0°C~50°C

NOTE

1.

500 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

110110. +00 1542475555.

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

