

# TEREZ PA 6.6 7500 GF 30 H

Polyamide 66  
TER HELL PLASTIC GMBH

Message:  
Medium viscosity standard Polyamide 6.6, 30% glass fibre reinforced, good flowability, good impact resistance and heat stabilised.  
For all kind of moulding parts wirh high stiffness at good heat resistance.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	Good Flow		
	Good Impact Resistance		
	Heat Stabilized		
	High Heat Resistance		
	High Stiffness		
	Medium Viscosity		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9900	MPa	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	80	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	240	°C	ISO 75-2/B
1.8 MPa, Unannealed	235	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT