Resinoid 7051

Phenolic

Resinoid Engineering Corporation

Message:

Resinoid 7051 is a Phenolic product filled with glass fiber. It can be processed by compression molding, injection molding, or resin transfer molding and is available in North America.

Characteristics include:

Good Dimensional Stability

Good Flexibility

General Information	
UL YellowCard	E61847-247066
Filler / Reinforcement	Glass Fiber
Features	Good Dimensional Stability
	Good Flexibility
Appearance	Black
Forms	Pellets
Processing Method	Compression Molding
	Injection Molding
	Resin Transfer Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.74	g/cm³	ASTM D792
Bulk Factor	2.0		ASTM D1895
Molding Shrinkage - Flow	0.10 to 0.20	%	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
E-Scale	100		
M-Scale	120		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	64.8	MPa	ASTM D638
Flexural Modulus	16500	MPa	ASTM D790
Flexural Strength (Yield)	165	MPa	ASTM D790
Compressive Strength	276	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8			
MPa, Unannealed)	271	°C	ASTM D648
CLTE - Flow	3.8E-5	cm/cm/°C	ASTM D696

Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	15	kV/mm	ASTM D149
Arc Resistance	180	sec	ASTM D495
Injection	Nominal Value	Unit	
Processing (Melt) Temp	149 to 182	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

