# **HIVOREX 7000F**

## High Density Polyethylene

### Lotte Chemical Corporation

#### Message:

7000F is manufactured to be processed in conventional blown film equipment by CSTR Slurry process technology.

Thanks to Bi-modal design of molecular composition, 7000F offer both excellent processability and superior mechanical properties.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Bimodal Molecular Weight Distribution		
	Good Processability		
Uses	Bags		
	Film		
	Packaging		
RoHS Compliance	RoHS Compliant		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.956	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	0.035	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (F50)	> 1000	hr	ASTM D1693
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	31.4	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	981	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	124	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

