Europrene® N 2845 GRN

Acrylonitrile Butadiene Rubber

Versalis S.p.A.

Message:

Europrene ® N 2845 GRN is an advanced technology cold polymerized acrylonitrile-butadiene copolymer made at the Porto Torres production facility in Italy. A non staining antioxidant is added during the production process.

Key Features

Europrene® N 2845 GRN is characterised by excellent processability and tear resistance at high temperature. GRN grades show higher cure rate, higher low temperature flexibility, higher crosslinking density and better mechanical properties, better oil and fuel resistance in comparison to STD grades. The improved processability guarantees low mould fouling products and then long production runs, lower mould wear and less production controls. The vulcanization can be performed by sulphur based systems or by peroxides. The low temperature properties can be improved by adding polar plasticizers as synthetic esters of adipic, sebacic or phtalic acids. To improve heat, light and ozone resistance, suitable protective agents as amine or phenolic antioxidants have to be added in the compounding process.

Main Applications

Grade with faster cure rate compared to equivalent standard type. Suitable for injection applications (low mould fouling)

| General Information | | | |
|----------------------------------|-----------------------------|------|-------------|
| Additive | Antioxidant | | |
| Features | Antioxidant | | |
| | Copolymer | | |
| | Fast Cure | | |
| | Fuel Resistant | | |
| | Good Processability | | |
| | Good Tear Strength | | |
| | Low Temperature Flexibility | | |
| | Oil Resistant | | |
| | | | |
| Appearance | Yellow | | |
| Forms | Bale | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Mooney Viscosity (ML 1+4, 100°C) | 45 | MU | ASTM D1646 |
| Acrylonitrile Content | 28.0 | wt% | ASTM D3533 |
| Ash Content | < 0.5 | wt% | ASTM D5667 |
| Organic Acid | < 0.5 | wt% | ASTM D5774 |
| Soap | < 0.6 | wt% | ASTM D5774 |
| Volatile Matter | < 0.70 | wt% | ASTM D5668 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

