HOPELEN J-150H

Polypropylene Homopolymer

Lotte Chemical Corporation

Message:

J-150H is homo polymer resin produced through the polymerization of propylene. This grade is designed to be processed in conventional injection molding equipment and offers high flow, high stiffness, heat stability, scratch resistance and high surface gloss.

General Information				
Features	Good Thermal Stability			
	High Flow			
	High Gloss			
	High Stiffness			
	Homopolymer			
	Scratch Resistant			
Uses	Appliances			
	Electrical/Electronic Applications			
	Toys			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	0.900	g/cm³	ASTM D792, ISO 1183	
Melt Mass-Flow Rate (MFR) (230°C/2.16				
kg)	12	g/10 min	ASTM D1238, ISO 1133	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	2.1.2			
Yield	34.3	MPa	ASTM D638	
Yield	32.4	MPa	ISO 527-2	
Tensile Elongation (Break)	> 100	%	ASTM D638, ISO 527-2	
Flexural Modulus				
	1620	MPa	ASTM D790	
	1270	MPa	ISO 178	
Impact	1270 Nominal Value	MPa Unit	ISO 178 Test Method	
Impact Notched Izod Impact	Nominal Value		Test Method	
Impact Notched Izod Impact -10°C	Nominal Value		Test Method ISO 180	
Impact Notched Izod Impact	Nominal Value 20 25	Unit	Test Method	
Impact Notched Izod Impact -10°C	Nominal Value	Unit J/m	Test Method ISO 180	
Impact Notched Izod Impact -10°C -10°C	Nominal Value 20 25	Unit J/m J/m	Test Method ISO 180 ASTM D256	
Impact Notched Izod Impact -10°C -10°C 23°C	Nominal Value 20 25 29	Unit J/m J/m J/m	Test Method ISO 180 ASTM D256 ASTM D256	
Impact Notched Izod Impact -10°C -10°C 23°C 23°C	Nominal Value 20 25 29 25	Unit J/m J/m J/m J/m	Test Method ISO 180 ASTM D256 ASTM D256 ISO 180	
Impact Notched Izod Impact -10°C -10°C 23°C 23°C Thermal	Nominal Value 20 25 29 25	Unit J/m J/m J/m J/m	Test Method ISO 180 ASTM D256 ASTM D256 ISO 180	

0.45 MPa, Unannealed	95.0	°C	ISO 75-2/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

