

Novalloy-B B2703

Acrylonitrile Butadiene Styrene + PBT

PlastxWorld Inc.

Message:

Novalloy-B B2703 is an acrylonitrile butadiene styrene + PBT (ABS + PBT) material, and its filler is 15% glass fiber reinforced material. This product is available in the Asia-Pacific region. The main characteristics of Novalloy-B B2703 are: flame retardant/rated flame.

General Information			
UL YellowCard	E47773-239629		
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.40 - 0.70	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	81.0	MPa	ISO 527-2
Flexural Modulus	5200	MPa	ISO 178
Flexural Stress	130	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C, 6.40 mm)	60	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 6.40mm	205	°C	ASTM D648
0.45 MPa, not annealed	205	°C	ISO 75-2/B
1.8 MPa, unannealed, 6.40mm	185	°C	ASTM D648
1.8 MPa, not annealed	160	°C	ISO 75-2/A
Linear thermal expansion coefficient			ISO 11359-2
Flow	3.0E-5	cm/cm/°C	ISO 11359-2
Lateral	1.0E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (1.50 mm)	35	kV/mm	ASTM D149
Comparative Tracking Index (CTI) (3.00 mm)	PLC 1		UL 746
Comparative Tracking Index (3.00 mm)	500	V	IEC 60112
High Amp Arc Ignition (HAI) (1.50 mm)	68.0		UL 746
High Amp Arc Ignition (HAI) (1.50 mm)	PLC 1		UL 746
High Voltage Arc Tracking Rate (HVTR) (3.00 mm)	1.20	mm/min	UL 746
High Voltage Arc Tracking Rate (HVTR) (3.00 mm)	PLC 0		UL 746

Hot-wire Ignition (HWI) (1.50 mm)	13	sec	UL 746
Hot-wire Ignition (HWI) (1.50 mm)	PLC 4		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 120	°C	
Drying Time	3.0 - 5.0	hr	
Rear Temperature	190 - 230	°C	
Middle Temperature	220 - 240	°C	
Front Temperature	240 - 250	°C	
Nozzle Temperature	230 - 250	°C	
Mold Temperature	60.0 - 80.0	°C	
Back Pressure	5.00 - 20.0	MPa	
Screw Speed	50 - 90	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

