

GERMAMID 6.6 FE 60

Polyamide 66
Kunststoff-Kontor-Hamburg GmbH

Message:
GERMAMID 6.6 FE 60 is a Polyamide 66 (Nylon 66) material. It is available in Europe.

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	2.15	g/cm ³	ISO 1183
Molding Shrinkage	0.50 to 0.90	%	ISO 294-4
Water Absorption (Saturation, 23°C)	0.60	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4000	MPa	ISO 527-2
Tensile Stress (Yield)	40.0	MPa	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Thermal	Nominal Value	Unit	
Melting Temperature	255	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT