

Telcar® TL-1445W

Thermoplastic Elastomer

Teknor Apex Company

Message:

Telcar TL-1445W is a UV resistant thermoplastic elastomer designed for the industrial market, specifically door and window seals. Telcar TL-1445W is a medium hardness, medium density TPE suitable for injection molding and extrusion.

General Information			
Features	Sunlight Resistant		
	smoothness		
	Light stabilization		
	Low liquidity		
	Lubrication		
	Fill		
	Medium density		
	Medium hardness		
	UV absorption		
Uses	Weather-resistant sealing strip		
	General		
Appearance	Opacity		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.50	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	69		ASTM D2240
Shaw A, 5 seconds	66		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
Transverse flow: 100% strain ¹	2.25	MPa	ASTM D412
Flow: 100% strain ²	5.44	MPa	ASTM D412
Transverse flow: 300% strain ³	3.39	MPa	ASTM D412
Tensile Strength ⁴			ASTM D412
Transverse flow: Fracture	9.74	MPa	ASTM D412

Flow: Fracture	6.42	MPa	ASTM D412
Tensile Elongation ⁵			ASTM D412
Transverse flow: Fracture	730	%	ASTM D412
Flow: Fracture	230	%	ASTM D412
Tear Strength ⁶			ASTM D624
Transverse flow	29.2	kN/m	ASTM D624
Flow	31.3	kN/m	ASTM D624
Compression Set ⁷			ASTM D395B
23°C, 22 hr	22	%	ASTM D395B
70°C, 22 hr	44	%	ASTM D395B

Injection	Nominal Value	Unit
Rear Temperature	171 - 193	°C
Middle Temperature	177 - 199	°C
Front Temperature	182 - 204	°C
Nozzle Temperature	188 - 210	°C
Processing (Melt) Temp	188 - 210	°C
Mold Temperature	25.0 - 65.6	°C
Injection Pressure	1.38 - 6.89	MPa
Injection Rate	Moderate-Fast	
Back Pressure	0.172 - 0.345	MPa
Screw Speed	50 - 100	rpm
Cushion	3.81 - 25.4	mm

Injection instructions

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	166 - 188	°C
Cylinder Zone 2 Temp.	171 - 193	°C
Cylinder Zone 3 Temp.	177 - 199	°C
Cylinder Zone 5 Temp.	182 - 204	°C
Die Temperature	190 - 210	°C

Extrusion instructions

Screw Speed: 30 to 100 rpm

NOTE

1. Mouth die C, 510mm/min
2. Mouth die C, 510mm/min
3. C mold, 510mm/min
4. C mold, 510mm/min
5. Mouth die C, 510mm/min
6. C mold, 510mm/min
7. Type 1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

