

Akulon® F136-E1

Polyamide 6
DSM Engineering Plastics

Message:

Akulon® F136-E1 is a polyamide 6 (nylon 6) material. This product is available in North America, Europe or Asia Pacific. The processing method is: film extrusion.

Akulon® The main features of the F136-E1 are:

nucleation
high viscosity
Lubrication

Akulon® The typical application fields of F136-E1 are: movies

General Information			
Additive	Nucleating agent		
	Lubricant		
Features	Nucleated		
	Lubrication		
	Viscosity, High		
Uses	Films		
Forms	Particle		
Processing Method	Film extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm³	ISO 1183
Viscosity Number	245	cm³/g	ISO 307
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ISO 8295
With itself-dynamic, cast film	0.80		ISO 8295
With itself-static, cast film	1.4		ISO 8295
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	
Tensile Modulus ¹ (50 µm, Cast Film)	465	MPa	Internal method
Tensile Stress - MD			ISO 527-3
Yield, 50 µm, cast film	34.0	MPa	ISO 527-3
50 µm, cast film	94.0	MPa	ISO 527-3
Tensile Elongation - MD (Broken, 50 µm, cast film)	350	%	ISO 527-3
Trouser Tear Resistance - MD (50 µm, Cast Film)	32.0	N/mm	ISO 6383-1
Water Vapor Transmission Rate (23°C, 85% RH, 50 µm, cast film)	35	g/m²/24 hr	DIS 15106-1/-3
Oxygen Transmission Rate ²			DIS 15105-1/-2

0% RH : 23°C, 50.0 μm	23	cm ³ /m ² /bar/24 hr	DIS 15105-1/-2
85% RH : 23°C, 50.0 μm	33	cm ³ /m ² /bar/24 hr	DIS 15105-1/-2
Specific Heat Capacity			
--	1550	J/kg/°C	
Average: 20 to 150°C	2250	J/kg/°C	
Puncture Resistance (50.0 μm) ³	13.2	J/cm	Internal method
RSV ⁴	3.60		Internal method
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	9.0E-5	cm/cm/°C	ISO 11359-2
Optical	Nominal Value	Unit	Test Method
Transmittance (50.0 μm, Cast Film)	85.0	%	Internal method
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (260°C)	2250	Pa · s	Internal method
Additional Information	Nominal Value	Unit	Test Method

Processing parameters for cast film test specimen:

Extruder Temperature: 270°C

Die Temperature: 270°C

Chill Roll Temperature: 110°C

Injection	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	4.0 - 8.0	hr
Rear Temperature	230 - 235	°C
Middle Temperature	235 - 250	°C
Front Temperature	240 - 260	°C
Nozzle Temperature	240 - 270	°C
Processing (Melt) Temp	240 - 275	°C
Mold Temperature	50.0 - 80.0	°C
Injection Rate	Moderate-Fast	
Back Pressure	3.00 - 10.0	MPa
Screw Compression Ratio	2.5:1.0	

NOTE

1. 50 mm/min
2. Cast Film
3. Cast Film
4. Formic Acid, 1g/100 ml

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

