

Andur 800 AP/Curene® 442

Polyurethane (Polyester/Polyether mix, TDI)

Anderson Development Company

Message:

Andur 800-AP is the result of several years of research to develop a high performance, moderate cost prepolymer for the cast urethane industry. This new product is a poly-ester/ether, toluene diisocyanate-terminated prepolymer. An elastomer with a hardness of 80 Shore A is obtained by reaction with Curene 442. Elastomers of lower hardness can be obtained by reaction with various polyols and their combination with Curene 442 and other diamines, or with plasticizers.

General Information			
Features	Solvent resistance		
	Hydrolysis stability		
Forms	Liquid		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ASTM D1505
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	80		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	4.14	MPa	ASTM D412
300% strain	7.14	MPa	ASTM D412
Tensile Strength (Yield)	38.6	MPa	ASTM D412
Tensile Elongation (Break)	500	%	ASTM D412
Compression Set	24	%	ASTM D395B
Bayshore Resilience	36	%	ASTM D2632
Thermoset	Nominal Value	Unit	
Pot Life	5.0 - 8.0	min	
Demold Time (100°C)	30	min	
Post Cure Time (100°C)	4.0	hr	

Additional Information

Durometer Hardness, ASTM D2240, Shore A: 78 to 82Die C Tear, ASTM D1004: 400 pliAverage Split Tear, ASTM D1938: 200 pliStoichiometry Curative Level: 95%Cure Time, 150 to 160°F: OvernightMix Temperature:
Andur 800 AP: 180-212°F
Curene 442: 250°F

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

