TECHLEN CM313

Polypropylene

DAEHA Co., LTD

Message:

TECHLEN CM313 is a Polypropylene material. It is available in Asia Pacific. Typical application of TECHLEN CM313: Automotive

| General Information | | | | |
|--------------------------------------|-------------------------|---------------------------|-------------|--|
| Features | Low Density | | | |
| Uses | Automotive Application | Automotive Applications | | |
| | Automotive Interior Par | Automotive Interior Parts | | |
| | | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 0.938 | g/cm³ | ASTM D792 | |
| Melt Mass-Flow Rate (MFR) | 28 | g/10 min | ASTM D1238 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Rockwell Hardness (R-Scale) | 75 | | ASTM D785 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength | 21.6 | MPa | ASTM D638 | |
| Tensile Elongation (Break) | 140 | % | ASTM D638 | |
| Flexural Modulus | 1770 | MPa | ASTM D790 | |
| Flexural Strength | 35.3 | MPa | ASTM D790 | |
| Impact | Nominal Value | Unit | Test Method | |
| Unnotched Izod Impact | | | ASTM D256 | |
| -10°C | 78 | J/m | | |
| 23°C | 200 | J/m | | |
| Thermal | Nominal Value | Unit | Test Method | |
| Deflection Temperature Under Load (0 | | | | |
| MPa, Unannealed) | 118 | °C | ASTM D648 | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

