Keliren® CM3680

Chlorinated Polyethylene

Mooney Viscosity (ML 1+4, 121°C)

Chlorine Content

75 to 85

35.0 to 37.0

Hangzhou Keli Chemical Co., Ltd.

Message:

Keliren® elastomers called rubber grades of CPE products are formulated into quality extruded, molded, and sheet rubber goods that satisfy critical needs for heat, oil and chemical resistance, compression set, toughness and durability, processibility, and value-related economics. Application: Wire & Cable, etc

Performance: Moderate Mooney viscosity and superior mechanical property

General Information		
Features	Durable	
	Flame Retardant	
	Good Chemical Resistance	
	Good Processability	
	Good Toughness	
	Good Weather Resistance	
	High Heat Resistance	
	Low Temperature Resistant	
	Medium Viscosity	
	Oil Resistant	
	Ozone Resistant	
	Soft	
Uses	Appliances	
	Automotive Applications	
	Cable Jacketing	
	Computer Components	
	Conveyors	
	Hose	
	Marine Applications	
	Mining Applications	
	Sheet	
	Wire & Cable Applications	
Processing Method	Extrusion	
	Injection Molding	
	Sheet Extrusion	
	Nominal Value Unit	Test Method

MU

wt%

ISO 289

ISO 7725

Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	< 57		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (Break)	> 8.00	MPa	ISO 37
Tensile Elongation (Break)	> 700	%	ISO 37

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

