

Matrixx P65E0

Polyamide 6
The Matrixx Group, Inc.

Message:

Matrixx P65E0 is a polyamide 6 (nylon 6) material. This product is available in North America.
The main features of Matrixx P65E0 are:
flame retardant/rated flame
Impact resistance

General Information			
Features	Impact resistance, high		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.8 - 2.4	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	46.2	MPa	ASTM D638
Flexural Modulus - Tangent	1790	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	800	J/m	ASTM D256
Dart Drop Impact	> 36.2	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
RTI	65.6	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.10	%	
Rear Temperature	243 - 282	°C	
Middle Temperature	243 - 282	°C	
Front Temperature	243 - 282	°C	
Processing (Melt) Temp	238 - 271	°C	
Mold Temperature	60.0 - 82.2	°C	
Injection Rate	Moderate		
Back Pressure	< 0.345	MPa	
Cushion	3.18 - 6.35	mm	
Injection instructions			

-20°C DewpointScrew Speed: Medium

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

