

POCAN® B 3215 XF 000000

Polybutylene Terephthalate

LANXESS Asia/Pacific

Message:

PBT, 10 % glass fibers, injection molding, improved flowability, improved impact strength

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Good Flow		
	Good Impact Resistance		
Agency Ratings	EC 1907/2006 (REACH)		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.34	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	30.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Across Flow : 260°C, 2.00 mm ¹	1.1	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.10	%	
Flow : 260°C, 2.00 mm ³	1.0	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4600	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	80.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	4.0	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	4250	MPa	ISO 178/A
Flexural Stress			ISO 178/A
3.5% Strain,23°C	120	MPa	
23°C ⁶	130	MPa	
Flexural Strain at Flexural Strength ⁷ (23°C)	4.9	%	ISO 178/A
ISO Shortname	PBT, GHMR, 09-050, GF10		ISO 7792
Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	30	kJ/m ²	
23°C	50	kJ/m ²	

Notched Izod Impact Strength			ISO 180/1A
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	30	kJ/m ²	
23°C	35	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	215	°C	ISO 75-2/B
1.8 MPa, Unannealed	180	°C	ISO 75-2/A
Vicat Softening Temperature	200	°C	ISO 306/B120
Melting Temperature ⁸	222	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	6.0E-5	cm/cm/°C	
Transverse : 23 to 55°C	1.4E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 to 8.0	hr	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 80°C MT, 600 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT